

# Standex 2K Special Matt makes simple Matt Refinishing.



1

**Defining the color and gloss level.**



2

**Preparing and cleaning the surface.**



3

**Applying the basecoat as per Technical Data Sheets.**



4

**Applying the 2K Special Matt ready to use clearcoat mixture in two carefully controlled overlapping coats with inter-coat flash-off 5 – 10 minutes.**



**Final flash-off 10 – 15 minutes.**



5

**Drying the matt clearcoat 45 – 50 minutes at 60°C object temperature.**



6

**Color and gloss level harmonize with the original!**

**STANDOX**

**The Art of Refinishing.**